

# DLG Test Report 7239

G. Spelsberg GmbH & Co. KG

## Junction box of the Abox-i series with accessories

Resistance to ammonia



G. SPELSBERG  
JUNCTION BOX OF THE ABOX-I  
SERIES WITH ACCESSORIES  
✓ Resistance to Ammonia  
DLG Test Report 7239



## Overview

A test mark “DLG-APPROVED for individual criteria” is awarded for agricultural products which have successfully fulfilled a scope-reduced usability testing conducted by DLG according to independent and recognised evaluation criteria. The test is intended to highlight particular innovations and key criteria of the test object. The test may contain criteria from the DLG test scope for overall tests, or focus on other value-determining characteristics and properties of the test subject. The minimum requirements, test conditions and procedures as well as the evaluation bases of the test results will be specified in consultation with an expert group of DLG. They correspond to the recognised rules of technology, as well as scientific and agricultural knowledge and requirements. The successful testing is concluded with the publication of a test report, as well as the awarding of the test mark which is valid for five years from the date of awarding.



**G. SPELSBERG  
JUNCTION BOX OF THE ABOX-I  
SERIES WITH ACCESSORIES**

✓ **Resistance to Ammonia**

DLG Test Report 7239

The DLG-APPROVED test “Ammonia resistance” includes technical examinations in the laboratory and in the NH<sub>3</sub> test chamber of the DLG Test Center Technology and Farm Inputs in Gross-Umstadt.

Brand-new samples of all materials used were tested. The testing was based on the DLG test specification for the study of ammonia resistance, version 2.4/2021.

Other criteria were not tested.

## Assessment in brief

The brand-new materials are tested regarding their ammonia resistance according to DLG-APPROVED test methods.

The tested materials have met the requirements regarding the examined criteria.

*Table 1:*  
*Overview of results*

DLG QUALITY PROFILE		Test result	Evaluation*
<b>Single Criteria Resistance to Ammonia</b>			
<b>Component</b> – Abox-i	empty housing	resistant	■ ■ ■ ■ □
– SNI	stepped nipple	resistant	■ ■ ■ ■ □
– AST	attachment spout	resistant	■ ■ ■ ■ □
– BST	ventilation spout	resistant	■ ■ ■ ■ □
– DMS	double membrane spout	resistant	■ ■ ■ ■ □
– DMS/sw	double membrane spout	resistant	■ ■ ■ ■ □
	insulating plug	resistant	■ ■ ■ ■ □

\* The DLG test framework provides the following options in its evaluation schemes:  
 ■ ■ ■ or better = meets, exceeds or clearly exceeds the specified DLG standard, ■ ■ = meets the legal requirements for marketability,  
 ■ = failed

## The Product

### Applicant and manufacturer

G. Spelsberg GmbH + Co. KG  
Im Gewerbepark 1  
D-58579 Schalksmühle  
Germany

### Product:

Junction Box Abox-i series with accessories

### Contact:

Phone +49 (0)2355 892-0  
Fax +49 (0)2355 892-299  
info@spelsberg.de  
www.spelsberg.de

### Description and technical data

The materials tested here are components of the junction box from the Abox-i series.

The box is also installed in animal houses, and can thus be exposed to elevated levels of ammonia in the housing environment.

### Table 2:

*Technical characteristics (according to manufacturer)*

Junction box Abox-i series		
Rated voltage		690 V
Rated current		57 A (125 A)
Length		110-250 mm
Width		110-250 mm
Height		67-115 mm
Rated connecting capacity		6-35 mm <sup>2</sup>
Accessories		Dimensions
SNI	stepped nipple	Ø 30 mm x 20 mm
AST	attachment spout	Ø 30 mm x 23 mm
BST	ventilation spout	Ø 25.5 mm x 13 mm
DMS	double membrane spout	Ø 25.5 mm x 14 mm
DMS/sw	double membrane spout	Ø 30 mm x 15 mm
	insulating plug	Ø 14 mm x 5 mm



Figure 2:  
DLG test lab – two ammonia chambers

### Resistance to ammonia

The ammonia resistance of the materials was determined by a laboratory testing according to the DLG test standard for agricultural use.

With the DLG laboratory test for NH<sub>3</sub> resistance, it is possible to determine the ability of the test sample to withstand the effects of animal house air over a usage period of about 10 years.

The test was carried out in a gassing chamber under the following climate conditions:

Test duration	1500 h
Air temperature	70 °C
Relative humidity	70 %
Ammonia concentration	750 ppm

For assessing the NH<sub>3</sub> resistance, the test samples were examined visually, gravimetrically and through a measurement of the material thickness before and after the climate testing.

The measurement of shore hardness only yielded relevant and tangible results for the accessory parts. The materials were tested on the basis of at least two samples.

## Detailed account of the test results

### Resistance to ammonia

During the test, all tested components and materials were resistant.

No visual or functional properties of the materials were restricted after the fumigation in the ammonia-containing environment.

All deviations of the measured parameters were within the measurement uncertainty or the evaluation thresholds. Thus, it can be assumed that the materials are able to sufficiently withstand a NH<sub>3</sub>-containing atmosphere, as it would be the case for exhaust air in pig houses for example.

Table 3:  
Change through the NH<sub>3</sub> exposure – junction box

Component	Visual assessment	Weight	Thickness	Evaluation
Box/cover with seal and screw	no change	0.2 %	–	resistant
Double membrane spout	no change	-0.8 %	< 0.1 %	resistant
<b>Junction box Abox-i series</b>				<b>resistant</b>

Table 4:  
Change through the NH<sub>3</sub> exposure – accessories

Accessories	Visual assessment	Weight	Shore hardness	Evaluation
SNI stepped nipple	no change	< 3.0 %	< 5.0 %	resistant
AST attachment spout	no change	< 3.0 %	< 5.0 %	resistant
BST ventilation spout	no change	< 3.0 %	< 5.0 %	resistant
DMS double membrane spout	no change	< 3.0 %	< 5.0 %	resistant
DMS/sw double membrane spout	no change	< 3.0 %	+ 6.5 %	resistant
insulating plug	no change	< 3.0 %	< 5.0 %	resistant

## Summary

The brand-new materials were tested regarding their ammonia resistance in the laboratory and in the NH<sub>3</sub> test chamber of the DLG Test Center Technology and Farm Inputs in Gross-Umstadt according to DLG-APPROVED test methods.

All tested materials have met the requirements regarding the examined criteria. Thus, the entire component is to be classified as resistant to ammonia-containing air.

## Further information

### Testing agency

DLG TestService GmbH,  
Gross-Umstadt location, Germany

The tests are conducted on behalf  
of DLG e.V.

### DLG test framework

DLG test specification  
“Ammonia resistance”, for light systems and  
stable equipments (version 2.4/2021)

### Department

Agriculture

### Division head

Dr. Ulrich Rubenschuh

### Test engineer(s)

Dipl.-Ing. (FH) Tommy Pfeifer\*

\* Author

## DLG – the open network and professional voice

Founded in 1885 by the German engineer Max Eyth, DLG (Deutsche Landwirtschafts-Gesellschaft – German Agricultural Society) is an expert organisation in the fields of agriculture, agribusiness and the food sector. Its mission is to promote progress through the transfer of knowledge, quality standards and technology. As such, DLG is an open network and acts as the professional voice of the agricultural, agribusiness and food sectors.

As one of the leading organisations in the agricultural and food market, DLG organises international trade fairs and events in the specialist areas of crop production, animal husbandry, machinery and equipment for farming and forestry work as well as energy supply and food technology. DLG’s quality tests for food, agricultural equipment and farm inputs are highly acclaimed around the world.

For more than 130 years, our mission has also been to promote dialogue between academia, farmers and

the general public across disciplines and national borders. As an open and independent organisation, our network of experts collaborate with farmers, academics, consultants, policymakers and specialists in administration in the development of future-proof solutions for the challenges facing the agriculture and the food industry.

### Leaders in the testing of agricultural equipment and input products

The DLG Test Center Technology and Farm Inputs and its test methods, test profiles and quality seals hold a leading position in testing and certifying equipment and inputs for the agricultural industry. Our test methods and test profiles are developed by an independent and impartial commission to simulate in-field applications of the products. All tests are carried out using state-of-the-art measuring and test methods applying also international standards.

Internal test code DLG: 2201-0013 (replaces DLG test report 6398)

Copyright DLG: © 2022 DLG



**DLG TestService GmbH**  
**Groß-Umstadt location**

Max-Eyth-Weg 1 • 64823 Groß-Umstadt • Germany  
Phone: +49 69 24788-600 • Fax: +49 69 24788-690  
Tech@DLG.org • www.DLG.org

Download of all  
DLG test reports free of charge  
at: [www.DLG-Test.de](http://www.DLG-Test.de)